FLEXICARB NR

PRODUCT

REFERENCE: Flexicarb NR

DESCRIPTION: Flexicarb NR is a high purity graphite laminate reinforced with a nickel foil core.

SERVICE: Flexicarb NR is recommended for general sealing applications and can be used

for sealing steam and most chemicals with the exception of oxidizing media. It is

particularly recommended where ease of gasket cutting is important.

Maximum recommended temperature: Oxidising media 370°C (700°F)

Inert or reducing media 1000°C (1830°F)

Maximum recommended pressure: 15 MPa (150 bar; 2200 psi)

Note: For applications sealing inert or reducing media, at temperatures in excess of 370°C, attention must be given to the possibility of oxidative attack on the

gasket from the external environment.

Use with strong oxidising agents should be avoided.

For long term continuous use in oxidising environments at temperatures in excess

of 370°C please consult our Applications Engineering Department.

CONSTRUCTION: Facing material: 98 % pure graphite foil.

Reinforcement: 13 micron nickel foil.

Adhesive: Polychloroprene.

TYPICAL PHYSICAL PROPERTIES:

Thickness		1.5 mm
Density	gcm-³	0.9
ASTM Compressibility	%	54
ASTM Recovery	%	10
BS Residual Stress	MPa	39
ASTM Tensile Strength	MPa	7
Leachable Chloride Ion Content	ppm	<50
Leachable Fluoride Ion Content	nnm	<50

AVAILABILITY:

Sheet size: 1.0 m x 1.0 m & 1.5 m x 1.5 m

Tolerances +5mm/-4mm

Thickness range: 1.0 mm to 3.0 mm

Tolerances +/- 10%

PDS 133 09/05

This Data Sheet refers to the material as supplied. The information contained herein is given in good faith, but no liability will be accepted by the Company in relation to same.

We reserve the right to change the details given on this Data Sheet as additional information is acquired. Customers requiring the latest version of this Data Sheet should contact our Applications Engineering Department.

The information given and, in particular, any parameters, should be used for guidance purposes only. The Company does not give any warranty that the product will be suitable for the use intended by the customer.

HEALTH AND SAFETY

Because of the processes which take place during manufacture, the product is believed to present no health and safety hazard and, under normal handling and use it is unlikely that the product will give rise to significant levels of exposure to constituent materials.

Flexicarb NR is a laminate containing exfoliated graphite reinforced with a nickel foil core.

Under harsh mechanical treatment (e.g. high speed stamping operations or abrasion) the constituents may give rise to irritant dusts which, in extreme cases of exposure, could lead to more serious respiratory problems. Occupational exposure to such dusts should therefore be minimised and kept below relevant national exposure limits. Good standards of hygiene should be applied during gasket cutting operations and off-cuts should be disposed of by transfer to a site appropriately licensed to accept industrial materials of this nature.

Graphite is combustible. At elevated temperatures or in a sustained fire, toxic fumes may be produced.

The material is conductive. Graphite debris or dust should not be allowed to penetrate electrical equipment. The reinforcing core may have very sharp edges; handle with care, particularly after cutting.

For more detailed information, reference must be made to our Health and Safety Bulletin, Sections 1, 2, 2.11, 3 and 3.2. This will enable you to carry out any necessary assessment of risk which may be required under national or local legislation.

CALL 832-445-0000

FAX 832-445-0002

EMAIL sales@flexsealindustrial.com

VISIT www.flexsealindustrial.com

24/7 EMERGENCY CALLOUT SERVICE

Flexseal Industrial is a full line gasket and o-ring distributor. We provide a broad range of products including but not limited to Flexitallic spiral wound gaskets, die cut gaskets, sheet material, Flexpro (kammprofile) gaskets, RTJ's and o-ring seals.

We offer superior customer service and are committed to meeting the needs of all your industrial sealing applications.

