

SF 5000 is an NBR bound sheet reinforced with carbon and aramid fibers. SF 5000 is suitable for use in a wide range of industrial applications including oils, fuels, steam, water and dilute acids. SF 5000 is especially suitable for sealing caustic liquors. Properties based on 1/32" thick material, except as otherwise noted.

**SERVICE**

Max T (at min. thickness)	824°F (440°C)
Max P (at min. thickness)	2030 psi (14.0 MPa)
pH Range	3 - 14

**PHYSICAL PROPERTIES**

Color	Black
Density	100 lb/ft <sup>3</sup> (1.60g/cc)
Sheet Thickness	1/64" - 1/8" (0.50 mm - 3.20 mm)
Sheet Size	60" x 60", 60" x 120" (1.50 m x 1.50 m, 1.5 m x 3.0 m)

**MECHANICAL PROPERTIES (ASTM F152)**

Cross Grain Tensile	2625 psi (18.1 MPa)
With Grain Tensile	7005 psi (48.3 MPa)

**IMMERSION PROPERTIES (ASTM F146)**

Thickness Increase	Oil #3 @ 300°F	3%
	Fuel B @ 70 - 85°F	5%
Weight Increase	Oil #3 @ 300°F	10%
	Fuel B @ 70 - 85°F	12%

**SEALING PROPERTIES**

ASTM F36J	Compressibility	7.5%
	Recovery	64%
ASTM F37A	Fuel A @ 50 psi & 1000 psi Gasket Stress	0.87 mL/hr
ASTM F38	Creep Relaxation	22.2%
BS 7531	Nitrogen Gas Permeability	0.05 mL/min

# COMPRESSED FIBER SHEET

# SF 5000

# PRODUCT PROFILE


## DESIGN INFORMATION

Gasket Constants	m	3.7
	y	3335 psi (23.00 MPa)
PVRC Constants (1/16" thick)	Gb	N/A
	a	N/A
	Gs	N/A
Recommended Surface Finish	125-250 µin (3.2 - 6.3 µm)	
Dielectric Strength	N/A	
ASTM Callout	712120M6†	† some digits may be chosen differently

## PRESSURE CONTAINMENT AND TEMPERATURE

SF 5000 Thickness (in.)	0.020	0.030	1/16	0.080	1/8
Max. Temperature (°F)	824	806	752	662	392
Max. Pressure (psi)	2030	1800	1305	1015	435

NOTE: Above pressure/temperature cannot be used simultaneously.



This Data Sheet relates to the material as supplied. The information contained herein is given in good faith, but no liability will be accepted by the Company in relation to same. The acquisition of additional information may necessitate revisions to parts or all of this Data Sheet, and such information will be supplied as it becomes available.

As the Company's products are used for a multiplicity of purposes, and as the Company has no control over the method of their application or use, the Company excludes all conditions or warranties, express or implied, by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the Company and the Customer is given for the Customer's assistance only and without liability on the part of the Company.



# FLEXSEAL INDUSTRIAL

A FULL LINE GASKET & O-RING SUPPLIER

A Flexitallic® Distributor

**CALL** 832-445-0000

**FAX** 832-445-0002

**EMAIL** [sales@flexsealindustrial.com](mailto:sales@flexsealindustrial.com)

**VISIT** [www.flexsealindustrial.com](http://www.flexsealindustrial.com)

## 24/7 EMERGENCY CALLOUT SERVICE

Flexseal Industrial is a full line gasket and o-ring distributor. We provide a broad range of products including but not limited to Flexitallic spiral wound gaskets, die cut gaskets, sheet material, Flexpro (kammprofile) gaskets, RTJ's and o-ring seals.

We offer superior customer service and are committed to meeting the needs of all your industrial sealing applications.

### SPIRAL WOUND GASKETS




**SIGMA**



**Thermiculite**  
innovative. versatile. complete.



**Flexpro™**



**-RINGS**